

Sonnenschein A500 / A506/10S

INDUSTRIAL BATTERIES / NETWORK POWER

Batteries of the Sonnenschein A500 range provide high capacities for many different applications. This range has been successfully in use for over twenty years in many installations worldwide. The success of A500 batteries comes from the superior dryfit technology, available in a wide range of models to provide a solution for every power need.

Part Number: NGA5060010HS0SA



APPLICATIONS



SPECIFICATIONS

- Excellent energy storage capacity combined with high reliability
- Grid plate construction with high quality lead calcium alloy, specially designed for enhanced energy density
- Very low gassing due to the internal gas recombination
- Design life: »10-12 Years – Long Life« according to EUROBAT 2015 classification
- Shelf life up to 2 years at 20 °C without recharge due to the very low self discharge rate
- Superior cycling performance
- Designed in accordance with IEC 60896-21/-22
- Approval: UL (Underwriter Laboratories)
- Trouble-free transport of operational blocks, no restrictions for rail, road, sea and air transportation (IATA, DGR, clause A67)
- Manufactured in Europe in our ISO 9001 certified production plants



Design life
10 - 12 years
- Long Life



Block
battery



Grid plate



Recyclable



Valve
regulated
lead-acid
batteries



Proof
against deep
discharge



Maintenance
free (no
topping up)

RECYCLE WITH EXIDE.



Exide Technologies takes pride in its commitment to a better environment. An integrated approach to manufacturing, distributing and recycling of leadacid batteries has been developed to ensure a safe and responsible life cycle for all of its products.



For more information please
[contact your local dealer](#)

TECHNICAL CHARACTERISTICS AND DATA

Nominal voltage	6 V
Float charge	2,3 V/C @ 20 °C
Capacity	CP 10min 1,6V/C 20°C 144W/Bloc CC 10h 1,8V/C 20°C 10Ah
Short circuit current	189 A (IEC60896-21/22)
Internal resistance	34 mΩ (IEC60896-21/22)

Terminal	S-4.8
Container	ABS
Temperature range	-40°C to 55°C
Dimensions (l x b/w x h)	152 x 50,5 x 98,4 mm
Weight	2,1 kg
Origin	Castanheira, Portugal


CONSTANT POWER DISCHARGE

W @ 20 °C	3 min	5 min	10 min	15 min	20 min	30 min	45 min	1 h	90 min
1,850 V/C	167	149	124	98	80	60	49	39	28
1,800 V/C	168	159	131	104	86	64	51	41	29
1,750 V/C	181	173	135	109	90	66	51	42	30
1,700 V/C	193	180	139	113	92	67	52	42	30
1,650 V/C	205	186	142	114	93	68	52	42	30
1,600 V/C	218	190	144	115	94	68	52	42	30

CONSTANT CURRENT DISCHARGE

A @ 20 °C	5 min	10 min	15 min	20 min	30 min	1 h	2 h	3 h	5 h	8 h	10 h
1,850 V/C	30	22	18	15	11,2	6,4	3,9	2,8	1,8	1,18	0,96
1,800 V/C	33	24	19	16	11,9	6,8	4,1	2,9	1,9	1,23	1
1,750 V/C	35	26	20	17	12,3	6,9	4,2	3	1,9	1,25	1,02
1,700 V/C	37	27	20	17	12,6	7	4,2	3	1,9	1,25	1,02
1,650 V/C	39	28	21	17	12,7	7,1	4,3	3	1,9	1,25	1,02
1,600 V/C	42	29	21	17	12,8	7,1	4,3	3	1,9	1,25	1,02

Technical drawing



Float Voltage vs Temperature

