

Sonnenschein A500 / A506/6,5S

INDUSTRIAL BATTERIES / NETWORK POWER

Batteries of the Sonnenschein A500 range provide high capacities for many different applications. This range has been successfully in use for over twenty years in many installations worldwide. The success of A500 batteries comes from the superior dryfit technology, available in a wide range of models to provide a solution for every power need.

Part Number: NGA50606D5HS0SA



APPLICATIONS



SPECIFICATIONS

- Excellent energy storage capacity combined with high reliability
- Grid plate construction with high quality lead calcium alloy, specially designed for enhanced energy density
- Very low gassing due to the internal gas recombination
- Design life: »10-12 Years – Long Life« according to EUROBAT 2015 classification
- Shelf life up to 2 years at 20 °C without recharge due to the very low self discharge rate
- Superior cycling performance
- Designed in accordance with IEC 60896-21/-22
- Approval: UL (Underwriter Laboratories)
- Trouble-free transport of operational blocks, no restrictions for rail, road, sea and air transportation (IATA, DGR, clause A67)
- Manufactured in Europe in our ISO 9001 certified production plants



Design life
10 - 12 years
- Long Life



Block
battery



Grid plate



Recyclable



Valve
regulated
lead-acid
batteries



Proof
against deep
discharge



Maintenance
free (no
topping up)

RECYCLE WITH EXIDE.



Exide Technologies takes pride in its commitment to a better environment. An integrated approach to manufacturing, distributing and recycling of leadacid batteries has been developed to ensure a safe and responsible life cycle for all ofits products.



For more information please
[contact your local dealer](#)

TECHNICAL CHARACTERISTICS AND DATA

Nominal voltage	6 V
Float charge	2,3 V/C @ 20 °C
Capacity	CP 10min 1,6V/C 20°C 92W/Bloc CC 10h 1,8V/C 20°C 6,3Ah
Short circuit current	131 A (IEC60896-21/22)
Internal resistance	48 mΩ (IEC60896-21/22)

Terminal	S-4.8
Container	ABS
Temperature range	-40°C to 55°C
Dimensions (l x b/w x h)	152 x 34,5 x 98,4 mm
Weight	1,3 kg
Origin	Castanheira, Portugal


CONSTANT POWER DISCHARGE

W @ 20 °C	3 min	5 min	10 min	15 min	20 min	30 min	45 min	1 h	90 min
1,850 V/C	120	100	73	60	51	38	28	23	16
1,800 V/C	128	112	80	63	54	40	30	24	17
1,750 V/C	138	121	86	66	57	42	30	24	17
1,700 V/C	150	126	88	68	58	42	31	24	17
1,650 V/C	160	129	90	69	59	43	31	25	18
1,600 V/C	168	132	92	70	59	43	31	25	18

CONSTANT CURRENT DISCHARGE

A @ 20 °C	5 min	10 min	15 min	20 min	30 min	1 h	2 h	3 h	5 h	8 h	10 h
1,850 V/C	17	12	10	8,1	6,1	3,6	2,1	1,5	1,1	0,73	0,61
1,800 V/C	19	13	11	8,8	6,5	3,8	2,2	1,6	1,1	0,75	0,63
1,750 V/C	20	14	11	9,2	6,8	3,9	2,3	1,6	1,1	0,76	0,63
1,700 V/C	21	15	12	9,5	6,9	3,9	2,3	1,6	1,1	0,76	0,63
1,650 V/C	23	15	12	9,6	7	4	2,3	1,6	1,1	0,76	0,63
1,600 V/C	24	16	12	9,7	7	4	2,3	1,6	1,1	0,76	0,63

Technical drawing



Float Voltage vs Temperature

